

## **EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings**

### **1 Point**

#### **Intent**

Reduce the quantity of indoor air contaminants that are odorous, irritating and/or harmful to the comfort and well-being of installers and occupants.

#### **Requirements**

Paints and coatings used on the interior of the building (defined as inside of the weatherproofing system and applied on-site) shall comply with the following criteria:

- Architectural paints, coatings and primers applied to interior walls and ceilings: Do not exceed the VOC content limits established in Green Seal Standard GS-11, Paints, First Edition, May 20, 1993.
  - Flats: 50 g/L
  - Non-Flats: 150 g/L
- Anti-corrosive and anti-rust paints applied to interior ferrous metal substrates: Do not exceed the VOC content limit of 250 g/L established in Green Seal Standard GC-03, Anti-Corrosive Paints, Second Edition, January 7, 1997.
- Clear wood finishes, floor coatings, stains, and shellacs applied to interior elements: Do not exceed the VOC content limits established in South Coast Air Quality Management District (SCAQMD) Rule 1113, Architectural Coatings, rules in effect on January 1, 2004.
  - Clear wood finishes: varnish 350 g/L; lacquer 550 g/L
  - Floor coatings: 100 g/L
  - Sealers: waterproofing sealers 250 g/L; sanding sealers 275 g/L; all other sealers 200 g/L
  - Shellacs: Clear 730 g/L; pigmented 550 g/L
  - Stains: 250 g/L

#### **Potential Technologies & Strategies**

Specify low-VOC paints and coatings in construction documents. Ensure that VOC limits are clearly stated in each section of the specifications where paints and coatings are addressed. Track the VOC content of all interior paints and coatings during construction.